

VC 17m Extra - Graphite

Antifouling

Low Friction, Thin Film Antifouling.High Strength Formula



PRODUCT DESCRIPTION

VC 17m Extra is high strength hard performance antifouling with a fluoro microadditive that gives your hull a slick low friction surface for maximum speed and efficiency, making it the ideal choice for racing yachts, powerboats and active craft.

- * Self-levels to a smooth even finish without the need to sand
- * Dries fast allowing you to paint and launch in the same day
- * Forms only a thin film so there's minimal paint build up with time
- * Suitable for use (with recommended primers) on GRP, Steel and Lead surfaces

PRODUCT INFORMATION

Colour	YBA762-Graphite
Finish	Matt
Specific Gravity	1.11
Volume Solids	11%
Converter/Curing Agent	YBA634 - 750 ml; YBA674 - 2 lt
Typical Shelf Life	2 yrs
VOC (As Supplied)	771 g/lt
Unit Size	750 ml 2.0 Lt

DRYING/OVERCOATING INFORMATION

	Drying			
	5°C (41°F)	15°C (59°F)	23°C (73°F)	35°C (95°F)
Immersion	30 mins	25 mins	20 mins	20 mins
Touch Dry	15 mins	15 mins	10 mins	5 mins
Pot Life	2 hrs	2 hrs	2 hrs	2 hrs

Note: Max. Immersion Times are as follows: 5-35°C/40-95°F - 12 months

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
VC 17m Extra - Graphite	30 mins	ext	25 mins	ext	20 mins	ext	20 mins	ext

APPLICATION AND USE

Preparation	<p>OLD VC 17m Wash down with fresh water.</p> <p>OTHER ANTIFOULINGS Remove eroding/copolymer types; or sand hard antifouling with 240 grade paper.</p> <p>BARE GRP Use VC General Thinner to clean and fully degrease the surface. Lightly sand with 240 grade paper. Rinse with fresh water and allow to dry. Use VC Tar2 to prime and protect against osmosis.</p> <p>STEEL Prime with VC Tar2 to prevent corrosion.</p> <p>LEAD Prime with VC Tar2.</p>
Method	Apply 2-3 coats on the area to be coated per season. In very high fouling conditions, the more paint applied, the better the performance. 3 full coats are recommended for optimal performance when applying direct to VC Tar 2 Primer.
Hints	<p>Mixing The paint MUST be applied within 2 hours of mixing. Shake base well prior to stirring in powder. Pour the powder (stored under the plastic hat) into the can. Stir or shake thoroughly. The can is large enough to allow easy stirring. Ensure paint is stirred regularly to avoid settlement.</p> <p>Thinner YTA600 VC General Thinner.</p> <p>Thinning VC 17m Extra - Graphite dries very quickly - small additions of VC General Thinner may be used to ease application.</p> <p>Cleaner YTA600 VC General Thinner. VC General Thinner can be used to remove splashes of VC 17m Extra - Graphite from the topsides.</p> <p>Roller Apply with a 4inch/100mm short mohair or foam roller.</p> <p>Other True colour will develop after immersion. Take care to apply all the paint calculated even if it means applying an extra coat. It is important for performance to ensure that uniform film is achieved and the recommended number of coats are applied.</p>
Some Important Points	To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide. Product

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2015.

VC 17m Extra - Graphite

Antifouling

Low Friction, Thin Film Antifouling, High Strength Formula



temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 1°C above dew point and maximum 35°C. Care should be taken to ensure that any metal based parts of the hull are suitably primed prior to application of VC 17m Extra - Graphite. Direct contact with VC 17m Extra - Graphite may result in corrosion or premature failure of the antifouling.

Warning: Only apply VC 17m Extra - Graphite in well ventilated areas or outdoors.

Compatibility/Substrates	Suitable for use (with recommended primers) on GRP, Steel, Wood and Lead surfaces. Not suitable for use over Aluminium/Alloy substrates.
Number of Coats	2-3
Coverage	(Theoretical) - 11 m ² /lt
Application Methods	Roller, DO NOT SPRAY

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of VC 17m Extra - Graphite to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.</p> <p>TRANSPORTATION: VC 17m Extra - Graphite should be kept in securely closed containers during transport and storage.</p>
Safety	<p>GENERAL: Contains biocides. Antifouling should only be wet sanded. Never dry sand or burn-off old antifouling. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p>DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of VC 17m Extra - Graphite cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>
IMPORTANT NOTES	<p><i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i></p>

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2015.